



PHYSICAL PROPERTY DATA SHEET

3S FILM COMPOUND

Property	Typical Value	ASTM
Shore A 15 Sec. Duro Delay	84A	D-2240
Tensile Strength, psi	2700	D-638
Ultimate elongation	350 %	D-638
Tear Strength	490 lbf/in	D-624
Brittleness Temperature	1.4° F /-17° C	D-746
UV Resistance	Yes	
Spec. Gravity	1.24	D-792
Biocide Additive	Yes (For Mildew Resistance)	

The information contained herein is believed to be reliable but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small scale equipment and does not necessarily indicate end product performance. Full scale testing and product performance are the responsibility of the user. Win Plastics (a division of TMI International, LLC) shall not be liable for, and the customer assumes all risk and liability of any use or handling of any material.

SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

TMI Int'l, LLC – 3333 Win Street, Cuyahoga Falls, Ohio 44223. Tel: 330-929-1999; Fax: 330-929-9698;
Web: <http://www.tmi-pvc.com>